

Technical Data Sheet



SAGA Pack 38 WS

Greaseproof paper made of bleached pulp and surface sized with wax, wet strength.

Food Contact, Quality and Environment

Production mill is certificated according ISO 9001, ISO 14001, ISO 50001, OHSAS 18001 , BRC-CP, IFS-HPC and PEFC/FSC (COC standards).

Products fulfil Kosher, Halal, Nordic Swan and the requirements of Code of Federal Regulations, Food an Drugs (FDA), 21 CFR CH 1 and the requirements of German Recommendation XXXVI and XXXVI/2 also Regulation No 1935/2004, Décret No 92-631 and compostability according to EN 13432.

Property	Unit	Test method	Typical values
Grammage	g/m ²	ISO 536	38.0 (36.0 – 40.0)
Moisture	%	ISO 287	5.5 (4.5 – 6.5)
ISO-Brightness	%	ISO 2470	75
Greaseproofness (Helga)	ml/h	Permeability Analyser	< 430
Cobb60	g/m ²	EN 20535	20
Tensile Strength MD	kN/m	ISO 1924-3	3.8
Tensile Strength D	kN/m	ISO 1924-3	1.6
Friction angle	°		11